UNITED STEEL SUPPLY

STANDARD COLOR OFFERINGS

Artic White
SR .69 SRI 84

Polar White
SR .64 SRI 77

Bone White
SR .61 SRI 72

Ivory
SR .69 SRI 84

Light Stone
SR .56 SRI 65

Saddle Tan
SR .47 SRI 53

Desert Sand
SR .42 SRI 47

Taupe
SR .38 SRI 41

Buckskin
SR .33 SRI 34

Burnished Slate
SR .34 SRI 35

Antique Bronze
SR .24 SRI 22

Light Brown
SR .38 SRI 41

Koko Brown
SR .35 SRI 37

Brown
SR .33 SRI 34

Black
SR .31 SRI 31

Ash Gray
SR .46 SRI 52

Old Town Gray
SR .41 SRI 45

Charcoal Gray
SR .37 SRI 31

Charcoal Gray II
SR .35 SRI 37

Charcoal Blue Gray
SR .29 SRI 29

Rustic Red
SR .36 SRI 38

Rural Red
SR .34 SRI 35

Dark Red
SR .36 SRI 39

Crimson Red
SR .31 SRI 31

Berry
SR .29 SRI 29

Evergreen
SR .35 SRI 37

Ivy Green
SR .28 SRI 27

Fern Green
SR .29 SRI 29

Colony Green
SR .28 SRI 27

Hawaiian Blue
SR .31 SRI 31

Gallery Blue
SR .26 SRI 24

Charcoal Gray CRINKLE
SR .33 SRI 35

Black CRINKLE
SR .29 SRI 29

Evergreen CRINKLE
SR .33 SRI 35

Rustic Red CRINKLE
SR .32 SRI 33

Burnished Slate CRINKLE
SR .30 SRI 31

Koko Brown CRINKLE
SR .33 SRI 34

Acrylic GALVALUME®
N/A

Copper Metallic
SR .51 SRI 58

PROUDLY FINISHED WITH
SHERWIN-WILLIAMS
Coil Coatings

> Final color selection should be made from actual color chips.

> For the most current information, visit **unitedsteelsupply.com**

> A 40-Year limited paint warranty is available for all colors upon written request. Please inquire. *(Outside the continental United States. please inquire).*

> Solar Reflectivity (SR): Solar reflectivity or reflectance is the measure of a materials ability to reflect solar energy or sunlight from its surface. SR values are numbered 0 to 1.0. A value of 0 indicates that the surface absorbs all solar energy and a alue of 1.0 indicates total reflectance. ENERGY STAR requires an SR value of 0.25 or higher for steep slope roofing (above 2:12) and an SR value of 0.65 or higher for low slope roofing (2:12 or less). For more information, please visit **energystar.gov**.

> Solar Refectance Index (SRI): The SRI is used to determine compliance with LEED requirements and is calculated according to ASTM E 1980 using values for reflectance and emissivity. To meet LEED requirements, a roofing material must have an SRI of 29 or greater for steep slope roofing and an SRI value of 78 or higher for low slope roofing. For more information, visit **usgbc.org**.

Standard Color Offerings

Color Name	29ga 40.8750 GR80 AZ50	26ga 41.5625 GR80 AZ50	26ga 41.5625 GR50 AZ50	26ga 20-20.5 GR50 AZ50	26ga 43.0000 GR80 AZ50
Acrylic GALVALUME®	●	●	●	●	●
Antique Bronze	●	□	□	□	□
Artic White	●	□	●	○	●
Ash Gray	●	●	●	○	●
Burnished Slate	●	●	●	○	●
Berry	●	●	●	○	●
Black	●	●	●	○	●
Bone White	●	●	●	○	●
Brown	●	●	●	○	●
Buckskin	●	□	□	□	□
Charcoal Gray	●	●	●	○	●
Charcoal Gray II	●	□	●	○	●
Charcoal Blue Gray	●	□	●	○	●
Colony Green	●	□	●	○	●
Copper Metallic	●	●	●	○	●
Crimson Red	●	●	●	○	●
Dark Red	●	□	□	□	□
Desert Sand	●	●	●	○	●
Evergreen	●	●	●	○	●
Fern Green	●	●	●	○	●
Gallery Blue	●	●	●	○	●
Haw Blue	●	●	●	○	●
Ivory	●	●	●	○	●
Ivy Green	●	●	●	○	●
Koko Brown	●	●	●	○	●
Light Brown	●	●	●	○	□
Light Stone	●	●	●	○	●
Old Town Gray	●	●	●	○	●
Polar White	●	●	●	○	●
Rural Red	●	●	●	○	●
Rustic Red	●	●	●	○	●
Saddle Tan	●	●	●	○	●
Taupe	●	●	●	○	●
Black CRINKLE	●	□	●	○	□
Burnished Slate CRINKLE	●	□	●	○	□
Charcoal Gray CRINKLE	●	□	●	○	□
Evergreen CRINKLE	●	□	●	○	□
Koko Brown CRINKLE	●	□	●	○	□
Rustic Red CRINKLE	●	□	●	○	□

● = Stock Color/Width ○ = Stock Color, 1-3 day slitting lead time □ = Paint-to-order, minimum required